QC ABSTRACT

NAME OF WORK: Improvements to Drains Cross Roads of Munigurappa Layout in Amruthahalli in Ward No.07 Byatarayanapura.

SL NO	Item Of Work	Name of Test	Frequency of Test/Quantity	Executed Quantity	Number of Tests Required	Number of Tests Conducted
		Materials				
1	Cement	Fineness by dry sieving	One Test		1	1
		Finess by Air permeablity method	One Test		1	1
		Density	One Test		1	1
		Standard Consistency	One Test		1	1
		Initial Setting time	One Test		1	1
		Final Setting time	One Test		1	1
		Soundness (Le Chatelier's Method)	One Test		1	1
		Compressive Strength	One Test		1	1
2	Coarse aggregate(40 mm down size)	SIEVE ANALYSIS	One Test		1	1
		Flakiness Index	One Test		1	1
		Elongation Index	One Test		1	1
		Specific Gravity	One Test		1	1
		Bulk Density(Loose)	One Test		1	1
		Bulk Density(Compacted)	One Test		1	1
		Water Absorption	One Test		1	1
3	Coarse aggregate(20 mm down size)	SIEVE ANALYSIS	One Test		1	1
		Flakiness Index	One Test		1	1
		Elongation Index	One Test		1	1
		Specific Gravity	One Test		1	1
		Bulk Density(Loose)	One Test		1	1
		Bulk Density(Compacted)	One Test		1	1
		Water Absorption	One Test		1	1
		Aggregate crushing Value	One Test		1	1
		Aggregate Impact Value	One Test		1	1
4	Fine aggregate	SIEVE ANALYSIS	One Test		1	1
		Water Absorption	One Test		1	1
		Specific Gravity	One Test		1	1
		Material finer than 75 micron	One Test		1	1
5	Steel	Bend test	One Test		1	1
		Tensile Test	One Test		1	1
		Yield Test	One Test		1	1
		ReBend test	One Test		1	1
6	KERB	Core Compressive strength	One Test		1	1
		Corrected Cylinder Compressive strength	One Test		1	1
		Equivalent Cube Compressive strength	One Test		1	1
7	PCC(M15)	Compressive Strength(7days and 28days)	5 set /51-100 cum	58.12	10	10

Ashok .N.D
AE(QC)

Assistant Engineer
Kodigehalli Division
Bruhat Bangalore Mahanagara Palike
Bangalore - 560 092

Format No: CP/TF/01

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID	:	**CP-2020-11-07-10** **Date: 24-08-20**
Customer	:	Assistant Executive Engineer, Kodigehalli Sub Division, BBMP, Bangalore.
Address	:	Kodigehalli Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to Drains Cross Roads of Munigurappa Layout in Amruthahalli in Ward No.07 Byatarayanapura.
Agency	:	M/ Sri. Channakeshawa Enterprises, Prop.Kiran Gowda D, No:882, 2nd Floor, Monika Nilaya, 13th Cross, Havanoor, Extn, Nagasandra Post, Bangalore-560073
Customer's Reference	:	BBMP/EE/BTP/WO/74/2020-21
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	20-08-20
Sample Type	:	Birla Super 53grade
Reference to BIS codes	:	IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification , IS 4031 (Part 1,2 3,4,5, 6,11):1988 IS 4031 Part 1 DETERMINATION OF FINENESS BY DRY SIEVING, Clause 4.4 IS 4031 Part 2, Determination of Fineness by Blaine Air Permeability Method, Clause 5 IS 4031 Part 3, Determination of Soundness, Clause 5,Clause 6 IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 5, Determination of Initial & Final Setting Time, Clause 5 IS 4031 Part 11,DETERMINATION OF DENSITY , Clause 6
Date of test	:	21-08-20
Environmental Conditions during test	:	Temperature: 26°C Humidity: 72%

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	Fineness by dry sieving (%)	1.08	–
2	Finess by Air permeablity method (m^2/kg,Min)	298.5	225m^2/kg, Min
3	Density (gm/cc)	3.13	–
4	Standard Consistency (%)	29.5%	Not specified
5	Initial Setting time	145 minutes	Not less than 30 minutes
6	Final Setting time	275 minutes	Not more than 600 minutes
7	Soundness (Le Chatelier's Method)	1.5mm	Not more than 10 mm

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.

All information furnished by Customer/Representative

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

AE(Ltd)

Bruhat Bangalore - 560 092

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID : **CP-2020-11-07-10** **Date: 18-09-20**

Customer : Assistant Executive Engineer, Kodigehalli Sub Division, BBMP, Bangalore.

Address : Kodigehalli Sub Division, BBMP, Bangalore.

Project Name : Improvements to Drains Cross Roads of Munigurappa Layout in Amruthahalli in Ward No.07 Byatarayanapura.

Agency : M/ Sri. Channakeshawa Enterprises, Prop.Kiran Gowda D, No:882, 2nd Floor, Monika Nilaya, 13th Cross, Havanoor, Extn, Nagasandra Post, Bangalore-560073

Customer's Reference : BBMP/EE/BTP/WO/74/2020-21

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 20-08-20

Sample Type : Birla Super 53grade

Reference to BIS codes : IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification ,
IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5
IS 4031 Part 6, Determination of Compressive Strength, Clause 6

Date of test : 21-08-20

Environmental Conditions during test : Temperature: 26°C
Humidity: 72%

Compressive Strength

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	3 Days	28.6N/mm^2	Not less than 27 N/mm^2
2	7 Days	39.4N/mm^2	Not less than 37 N/mm^2
3	28 Days	58.6N/mm^2	Not less than 53 N/mm^2

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

AE(Ltr)

Assistant Executive Engineer
Kodigehalli Sub Division
Bruhat Bangalore Mahanagara Palike
Bangalore - 560 092

CIVIL Pro Sig Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID	:	**CP-2020-11-07-10** **Date: 24-08-20**
Customer	:	Assistant Executive Engineer, Kodigehalli Sub Division, BBMP, Bangalore.
Address	:	Kodigehalli Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to Drains Cross Roads of Munigurappa Layout in Amruthahalli in Ward No.07 Byatarayanapura.
Agency	:	M/ Sri. Channakeshawa Enterprises, Prop.Kiran Gowda D, No:882, 2nd Floor, Monika Nilaya, 13th Cross, Havanoor, Extn, Nagasandra Post, Bangalore-560073
Customer's Reference	:	BBMP/EE/BTP/WO/74/2020-21
Source of Sample	:	Sample supplied by Agency
Sample condition	:	Satisfactory
Date of Receipt	:	20-08-20
Sample Type	:	40mm down size coarse aggregate
Reference to BIS codes	:	IS: 383:2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1,3,4) RA2011 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption IS 2386 Part 4: Mechanical Properties
Date of test	:	20-08-20

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 40MM DOWN COARSE AGGREGATE:

Total weight taken : 15000 grams

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	80 mm	0	0	0.0	100	100
2	40 mm	423	423	2.8	97.2	90-100
3	20 mm	5852	6275	41.8	58.2	30-70
4	10 mm	4232	10507	70.0	30.0	10-35
5	4.75 mm	4225	14732	98.2	1.8	0-5
6	Pan	268	15000	100.0	0	---

CIVIL Pro Sig..... Date..... BANGALORE

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID : **CP-2020-11-07-10** **Date: 24-08-20**

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS:383-2016
1	Flakiness Index(%)	12.3	Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate
2	Elongation Index(%)	11.6	
3	Specific Gravity	2.68	–
4	Bulk Density(Loose) (Kg/l)	1.56	–
5	Bulk Density(Compacted) (Kg/l)	1.59	–
6	Water Absorption(%)	0.23	–

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Asstt. Exe. Engineer
Kodigehalli Sub Division
Bruhat Bangalore Mahanagara Palike
Bangalore - 560 092

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID	:	**CP-2020-11-07-10** **Date: 24-08-20**
Customer	:	Assistant Executive Engineer, Kodigehalli Sub Division, BBMP, Bangalore.
Address	:	Kodigehalli Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to Drains Cross Roads of Munigurappa Layout in Amruthahalli in Ward No.07 Byatarayanapura.
Agency	:	M/ Sri. Channakeshawa Enterprises, Prop.Kiran Gowda D, No:882, 2nd Floor, Monika Nilaya, 13th Cross, Havanoor, Extn, Nagasandra Post, Bangalore-560073
Customer Reference	:	BBMP/EE/BTP/WO/74/2020-21
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	20-08-20
Sample Type/ Size	:	20mm down size coarse aggregate
Reference to BIS codes	:	IS: 383:2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1,3,4) RA2011 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption IS 2386 Part 4: Mechanical Properties
Date of test	:	20-08-20

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 20MM DOWN COARSE AGGREGATE:

Total weight taken : **5000** **grams**

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	40 mm	0	0	0	100	100
2	20 mm	278	278	5.6	94.4	90-100
3	10 mm	2754	3032	60.6	39.4	25-55
4	4.75 mm	1754	4786	95.7	4.3	0-10
5	Pan	214	5000	100	0	_

CIVIL PRO Sig..... Date..... BANGALORE

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID : **CP-2020-11-07-10** **Date: 24-08-20**

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS:383-2016
1	Flakiness Index(%)	12.2	Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate
2	Elongation Index(%)	11.7	
3	Specific Gravity	2.69	_
4	Bulk Density(Loose) (Kg/l)	1.53	_
5	Bulk Density(Compacted) (Kg/l)	1.54	_
6	Water Absorption(%)	0.25	_
7	Aggregate crushing Value(%)	23.3	Max 30% for Aggregates to be used in concrete for wearing Surface, In case Aggregate Crushing Value Exceeds 30% then the test for ten percent fines should be conducted for Aggregates to be used in concrete other than for wearing Surface.
8	Aggregate Impact Value(%)	22.7	30% for Aggregates to be used in concrete for wearing Surface, 45% for Aggregates to be used in concrete other than for wearing Surface.

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Assistant Engineer
Bruhat Bangalore Mahanagara Palike
Bangalore - 560 092

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signature
Quality Manager

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF FINE AGGREGATE

Lab ID : **CP-2020-11-07-10** **Date: 24-08-20**

Customer : Assistant Executive Engineer, Kodigehalli Sub Division, BBMP, Bangalore.

Address : Kodigehalli Sub Division, BBMP, Bangalore.

Project Name : Improvements to Drains Cross Roads of Munigurappa Layout in Amruthahalli in Ward No.07 Byatarayanapura.

Agency : M/ Sri. Channakeshawa Enterprises, Prop.Kiran Gowda D, No:882, 2nd Floor, Monika Nilaya, 13th Cross, Havanoor, Extn, Nagasandra Post, Bangalore-560073

Customer's Reference : BBMP/EE/BTP/WO/74/2020-21

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 20-08-20

Sample Type : Fine Aggregate

Reference to BIS codes : IS 383 : 2016 (Specification for Coarse and fine Aggregates)
IS: 2386 :1963(Part - 1, 3) RA2012
IS 2386 Part 1: Particle Size and Shape
IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption

Date of test : 20-08-20

Total weight taken : 1000 grams

Sl.no	Sieve Size	Weight Retained (gms)	Cumulative Weight Retained (gms)	% Cumulative Weight Retained	% Passing	Requirement as per IS 383:2016			
						Grading Zone I	Grading Zone II	Grading Zone III	Grading Zone IV
1	10 mm	0	0	0.0	100.0	100	100	100	100
2	4.75 mm	86	86	8.6	91.4	90-100	90-100	90-100	95-100
3	2.36 mm	145	231	23.1	76.9	60-95	75-100	85-100	95-100
4	1.18 mm	156	387	38.7	61.3	30-70	55-90	75-100	90-100
5	600 micron	188	575	57.5	42.5	15-34	35-59	60-79	80-100
6	300 micron	175	750	75.0	25.0	5-20	8-30	12-40	15-50
7	150 micron	162	912	91.2	8.8	0-10	0-10	0-10	0-15
8	Pan	88	1000	100.0	0.0	---	---	---	---

Result :The tested Sample Conforms to Grading Zone II

CIVIL Pro Sig..... Date..... BANGALORE

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

TEST REPORT OF FINE AGGREGATE

Lab ID : **CP-2020-11-07-10** **Date: 24-08-20**

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS 383:2016
1	Water Absorption(%)	2.4	–
2	Specific Gravity	2.59	–
3	Material finer than 75 micron(%)	5.9	Uncrushed fine Aggregate Max 3%, Crushed Fine aggregate Max 15%, Mixed Fine aggregate Max 12%, Manufactured Fine aggregate Max 10%

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Assistant Executive Engineer
Kodigehalli Division
Bruhat Bangalore Mahanagara Palike
Bangalore - 560 092

CIVIL PRO Sig. Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Format No: CP/TF/01

TEST RESULTS OF STEEL

Lab ID : **CP-2020-11-07-10** **Date: 21-08-20**

Customer : Assistant Executive Engineer, Kodigehalli Sub Division, BBMP, Bangalore.

Address : Kodigehalli Sub Division, BBMP, Bangalore.

Project Name : Improvements to Drains Cross Roads of Munigurappa Layout in Amruthahalli in Ward No.07 Byatarayanapura.

Agency : M/ Sri. Channakeshawa Enterprises, Prop.Kiran Gowda D, No:882, 2nd Floor, Monika Nilaya, 13th Cross, Havanoor, Extn, Nagasandra Post, Bangalore-560073

Customer's Reference : BBMP/EE/BTP/WO/74/2020-21

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 20-08-20

Sample Type : Sunvik

Reference to BIS codes : IS 1786-2008, IS:1608-2005(RA 2011), IS 1599-2012.

Date of test: : 20-08-20

Sl.No	Identification of sample	Grade of the sample	Diameter of the steel bar	Weight of the sample	Yield stress	Tensile strength	Elongation	Bend test	Rebend test
			(mm)	(kg/m)	(N/mm2)	(N/mm2)	(%)		
1	Sunvik	Fe500	8	0.391	512	652	20.0%	Satisfactory	Satisfactory
2	Sunvik	Fe500	10	0.616	528	672	20.0%	Satisfactory	Satisfactory
3	Sunvik	Fe500	12	0.888	544	668	20.0%	Satisfactory	Satisfactory

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig. Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

A.D.M.S. N.D. AE(Tech)

Assistant Executive Engineer Kodigehalli Sub Division Bruhat Bangalore Mahanagara Palike Bangalore - 560 092

End of Report

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE KERB STONE

Lab ID	:	**CP-2020-11-07-10** **Date: 22-09-20**
Customer	:	Assistant Executive Engineer, Kodigehalli Sub Division, BBMP, Bangalore.
Address	:	Kodigehalli Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to Drains Cross Roads of Munigurappa Layout in Amruthahalli in Ward No.07 Byatarayanapura.
Agency	:	M/ Sri. Channakeshawa Enterprises, Prop.Kiran Gowda D, No:882, 2nd Floor, Monika Nilaya, 13th Cross, Havanoor, Extn, Nagasandra Post, Bangalore-560073
Customer's Reference	:	BBMP/EE/BTP/WO/74/2020-21
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	18-09-20
Sample Type /Size	:	CC Kerb Stone/ 450*150*500mm
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete
Date of test	:	18/09/2020

Sl. No.	Identification Mark	Diameter of the core	Height of the core	Weight of the core	Area	Failure Load	Core Compressive strength	Corrected Cylinder Compressive strength	Equivalent Cube Compressive strength
		(mm)	(mm)	Kg	(Sq.mm)	(KN)	(N/mm2)	(N/mm2)	(N/mm2)
1	A	75.01	150.51	2.164	4418	132.1	29.9	29.9	37.4
2	B	75.03	150.49	2.193	4421	135.2	30.6	30.6	38.2
3	C	75.01	150.50	2.115	4418	135.1	30.6	30.6	38.2

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Assistant Executive Engineer
Kodigehalli Sub Division
Bruhat Bangalore Mahanagara Palike
Bangalore - 560 092

Sig.
Date
BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-11-07-10** **Date: 15/09/2020**

Customer : Assistant Executive Engineer, Kodigehalli Sub Division, BBMP, Bangalore.

Address : Kodigehalli Sub Division, BBMP, Bangalore.

Project Name : Improvements to Drains Cross Roads of Munigurappa Layout in Amruthahalli in Ward No.07 Byatarayanapura.

Agency : M/ Sri. Channakeshawa Enterprises, Prop.Kiran Gowda D, No:882, 2nd Floor, Monika Nilaya, 13th Cross, Havanoor, Extn, Nagasandra Post, Bangalore-560073

Customer's Reference : BBMP/EE/BTP/WO/74/2020-21

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 10-09-20

Customer ID : Copping Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M15 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 15/09/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Copping Concrete	M15	08/09/2020	15/09/2020	149.42 X 151.72 X 149.81	22670	8.361	283.4	12.5	12.5
2	Copping Concrete	M15	08/09/2020	15/09/2020	149.95 X 151.69 X 150.20	22745	8.676	286.5	12.6	
3	Copping Concrete	M15	08/09/2020	15/09/2020	151.22 X 149.73 X 149.30	22643	8.888	283.5	12.5	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

AE (W1)

Assistant Executive Engineer
Kodigehalli Sub Division
Bruhat Bangalore Mahanagara Palike
Bangalore - 560 092

CIVIL Pro Sig Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-11-07-10** **Date: 06/10/2020**

Customer : Assistant Executive Engineer, Kodigehalli Sub Division, BBMP, Bangalore.

Address : Kodigehalli Sub Division, BBMP, Bangalore.

Project Name : Improvements to Drains Cross Roads of Munigurappa Layout in Amruthahalli in Ward No.07 Byatarayanapura.

Agency : M/ Sri. Channakeshawa Enterprises, Prop.Kiran Gowda D, No:882, 2nd Floor, Monika Nilaya, 13th Cross, Havanoor, Extn, Nagasandra Post, Bangalore-560073

Customer's Reference : BBMP/EE/BTP/WO/74/2020-21

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 10-09-20

Customer ID : Copping Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M15 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 06/10/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Copping Concrete	M15	08/09/2020	06/10/2020	151.32 X 149.48 X 149.29	22620	**8.973**	404.3	17.9	
2	Copping Concrete	M15	08/09/2020	06/10/2020	151.09 X 149.01 X 149.67	22514	**8.629**	402.6	17.9	17.7
3	Copping Concrete	M15	08/09/2020	06/10/2020	150.70 X 151.37 X 151.28	22812	**8.352**	394.5	17.3	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

AE(NOL)

Assistant Executive Engineer
Kodigehalli Sub Division
Bruhat Bangalore Mahanagara Palike
Bangalore - 560 092

CIVIL Pro Sig. Date. BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-11-07-10** **Date: 15/09/2020**

Customer : Assistant Executive Engineer, Kodigehalli Sub Division, BBMP, Bangalore.

Address : Kodigehalli Sub Division, BBMP, Bangalore.

Project Name : Improvements to Drains Cross Roads of Munigurappa Layout in Amruthahalli in Ward No.07 Byatarayanapura.

Agency : M/ Sri. Channakeshawa Enterprises, Prop.Kiran Gowda D, No:882, 2nd Floor, Monika Nilaya, 13th Cross, Havanoor, Extn, Nagasandra Post, Bangalore-560073

Customer's Reference : BBMP/EE/BTP/WO/74/2020-21

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 10-09-20

Customer ID : Copping Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M15 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 15/09/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Copping Concrete	M15	08/09/2020	15/09/2020	150.92 X 149.99 X 151.83	22637	**8.361**	282.8	12.5	12.8
2	Copping Concrete	M15	08/09/2020	15/09/2020	150.27 X 149.02 X 150.95	22393	**8.676**	290.5	13.0	
3	Copping Concrete	M15	08/09/2020	15/09/2020	151.19 X 150.73 X 151.85	22788	**8.888**	292.6	12.8	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Assistant Executive Engineer
Kodigehalli Sub Division
Bruhat Bangalore Mahanagara Palike
Bangalore - 560 092

AE(W2)

CIVIL Pro Sig Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-11-07-10** **Date: 06/10/2020**

Customer : Assistant Executive Engineer, Kodigehalli Sub Division, BBMP, Bangalore.

Address : Kodigehalli Sub Division, BBMP, Bangalore.

Project Name : Improvements to Drains Cross Roads of Munigurappa Layout in Amruthahalli in Ward No.07 Byatarayanapura.

Agency : M/ Sri. Channakeshawa Enterprises, Prop.Kiran Gowda D, No:882, 2nd Floor, Monika Nilaya, 13th Cross, Havanoor, Extn, Nagasandra Post, Bangalore-560073

Customer's Reference : BBMP/EE/BTP/WO/74/2020-21

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 10-09-20

Customer ID : Copping Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M15 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 06/10/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Copping Concrete	M15	08/09/2020	06/10/2020	151.16 X 150.59 X 151.58	22763	8.973	387.8	17.0	17.3
2	Copping Concrete	M15	08/09/2020	06/10/2020	149.79 X 150.73 X 149.35	22578	8.629	387.4	17.2	
3	Copping Concrete	M15	08/09/2020	06/10/2020	149.53 X 150.54 X 149.59	22511	8.352	397.8	17.7	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

A.E.E. (M.D.)

Assistant Executive Engineer
Kodigehalli Sub Division
Bruhat Bangalore Mahanagara Palike
Bangalore - 560 092

CIVIL Pro Sig. Date. BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-11-07-10** **Date: 15/09/2020**

Customer : Assistant Executive Engineer, Kodigehalli Sub Division, BBMP, Bangalore.

Address : Kodigehalli Sub Division, BBMP, Bangalore.

Project Name : Improvements to Drains Cross Roads of Munigurappa Layout in Amruthahalli in Ward No.07 Byatarayanapura.

Agency : M/ Sri. Channakeshawa Enterprises, Prop.Kiran Gowda D, No:882, 2nd Floor, Monika Nilaya, 13th Cross, Havanoor, Extn, Nagasandra Post, Bangalore-560073

Customer's Reference : BBMP/EE/BTP/WO/74/2020-21

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 10-09-20

Customer ID : Copping Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M15 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 15/09/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Copping Concrete	M15	08/09/2020	15/09/2020	150.58 X 150.52 X 149.27	22664	**8.361**	277.9	12.3	12.2
2	Copping Concrete	M15	08/09/2020	15/09/2020	150.30 X 149.83 X 150.65	22519	**8.676**	274.1	12.2	
3	Copping Concrete	M15	08/09/2020	15/09/2020	149.07 X 149.68 X 149.86	22314	**8.888**	273.7	12.3	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

AE(Ker)

Assistant Executive Engineer
Kodigehalli Sub Division
Bruhat Bangalore Mahanagara Palike
Bangalore - 560 092

CIVIL Pro Sig. Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-11-07-10** **Date: 06/10/2020**

Customer : Assistant Executive Engineer, Kodigehalli Sub Division, BBMP, Bangalore.

Address : Kodigehalli Sub Division, BBMP, Bangalore.

Project Name : Improvements to Drains Cross Roads of Munigurappa Layout in Amruthahalli in Ward No.07 Byatarayanapura.

Agency : M/ Sri. Channakeshawa Enterprises, Prop.Kiran Gowda D, No:882, 2nd Floor, Monika Nilaya, 13th Cross, Havanoor, Extn, Nagasandra Post, Bangalore-560073

Customer's Reference : BBMP/EE/BTP/WO/74/2020-21

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 10-09-20

Customer ID : Copping Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M15 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 06/10/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Copping Concrete	M15	08/09/2020	06/10/2020	151.92 X 151.28 X 149.57	22982	**8.973**	395.0	17.2	17.6
2	Copping Concrete	M15	08/09/2020	06/10/2020	149.54 X 151.45 X 149.02	22648	**8.629**	405.4	17.9	
3	Copping Concrete	M15	08/09/2020	06/10/2020	149.42 X 149.56 X 149.44	22347	**8.352**	396.1	17.7	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Ashwin. N.D.
AE (Civil)

Assistant Executive Engineer
Kodigehalli Sub Division
Bruhat Bangalore Mahanagara Palike
Bangalore - 560 092

CIVIL PRO Sig. Date. BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1
****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-11-07-10** **Date: 15/09/2020**

Customer : Assistant Executive Engineer, Kodigehalli Sub Division, BBMP, Bangalore.

Address : Kodigehalli Sub Division, BBMP, Bangalore.

Project Name : Improvements to Drains Cross Roads of Munigurappa Layout in Amruthahalli in Ward No.07 Byatarayanapura.

Agency : M/ Sri. Channakeshawa Enterprises, Prop.Kiran Gowda D, No:882, 2nd Floor, Monika Nilaya, 13th Cross, Havanoor, Extn, Nagasandra Post, Bangalore-560073

Customer's Reference : BBMP/EE/BTP/WO/74/2020-21

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 10-09-20

Customer ID : Copping Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M15 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 15/09/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Copping Concrete	M15	08/09/2020	15/09/2020	149.38 X 150.50 X 150.02	22483	**8.361**	290.9	12.9	12.7
2	Copping Concrete	M15	08/09/2020	15/09/2020	149.38 X 149.16 X 150.50	22280	**8.676**	268.7	12.1	
3	Copping Concrete	M15	08/09/2020	15/09/2020	150.30 X 151.86 X 151.55	22824	**8.888**	296.6	13.0	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

AE(Ltd)

Assistant Executive Engineer
Kodigehalli Sub Division
Bruhat Bangalore Mahanagara Palike
Bangalore - 560 016

FOR CIVIL Pro.

CIVIL Pro Sig. Date BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-11-07-10** **Date: 06/10/2020**

Customer : Assistant Executive Engineer, Kodigehalli Sub Division, BBMP, Bangalore.

Address : Kodigehalli Sub Division, BBMP, Bangalore.

Project Name : Improvements to Drains Cross Roads of Munigurappa Layout in Amruthahalli in Ward No.07 Byatarayanapura.

Agency : M/ Sri. Channakeshawa Enterprises, Prop.Kiran Gowda D, No:882, 2nd Floor, Monika Nilaya, 13th Cross, Havanoor, Extn, Nagasandra Post, Bangalore-560073

Customer's Reference : BBMP/EE/BTP/WO/74/2020-21

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 10-09-20

Customer ID : Copping Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M15 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 06/10/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Copping Concrete	M15	08/09/2020	06/10/2020	151.80 X 150.96 X 151.33	22917	**8.973**	411.9	18.0	17.8
2	Copping Concrete	M15	08/09/2020	06/10/2020	149.41 X 149.13 X 151.41	22282	**8.629**	396.6	17.8	
3	Copping Concrete	M15	08/09/2020	06/10/2020	150.93 X 150.36 X 149.93	22694	**8.352**	397.0	17.5	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

AE(ADP)

Assistant Executive Engineer
Kodigehalli Sub Division
Bruhat Bangalore Mahanagara Palike
Bangalore - 560 0

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-11-07-10** **Date: 15/09/2020**

Customer : Assistant Executive Engineer, Kodigehalli Sub Division, BBMP, Bangalore.

Address : Kodigehalli Sub Division, BBMP, Bangalore.

Project Name : Improvements to Drains Cross Roads of Munigurappa Layout in Amruthahalli in Ward No.07 Byatarayanapura.

Agency : M/ Sri. Channakeshawa Enterprises, Prop.Kiran Gowda D, No:882, 2nd Floor, Monika Nilaya, 13th Cross, Havanoor, Extn, Nagasandra Post, Bangalore-560073

Customer's Reference : BBMP/EE/BTP/WO/74/2020-21

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 10-09-20

Customer ID : Copping Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M15 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 15/09/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Copping Concrete	M15	08/09/2020	15/09/2020	149.35 X 150.57 X 151.90	22487	8.361	283.6	12.6	12.6
2	Copping Concrete	M15	08/09/2020	15/09/2020	150.72 X 150.74 X 150.16	22720	8.676	292.7	12.9	
3	Copping Concrete	M15	08/09/2020	15/09/2020	150.02 X 151.53 X 149.70	22733	8.888	278.6	12.3	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

AE (WS)

Assistant Executive Engineer
Kodigehalli Sub Division
Bruhat Bangalore Mahanagara Palike
Bangalore - 560 0

CIVIL Pro Sig Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-11-07-10** **Date: 06/10/2020**

Customer : Assistant Executive Engineer, Kodigehalli Sub Division, BBMP, Bangalore.

Address : Kodigehalli Sub Division, BBMP, Bangalore.

Project Name : Improvements to Drains Cross Roads of Munigurappa Layout in Amruthahalli in Ward No.07 Byatarayanapura.

Agency : M/ Sri. Channakeshawa Enterprises, Prop.Kiran Gowda D, No:882, 2nd Floor, Monika Nilaya, 13th Cross, Havanoor, Extn, Nagasandra Post, Bangalore-560073

Customer's Reference : BBMP/EE/BTP/WO/74/2020-21

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 10-09-20

Customer ID : Copping Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M15 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 06/10/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Copping Concrete	M15	08/09/2020	06/10/2020	150.90 X 149.58 X 151.76	22572	8.973	391.3	17.3	17.4
2	Copping Concrete	M15	08/09/2020	06/10/2020	149.42 X 149.46 X 150.45	22332	8.629	389.5	17.4	
3	Copping Concrete	M15	08/09/2020	06/10/2020	150.42 X 149.92 X 149.97	22550	8.352	392.6	17.4	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

AE(W2)

Assistant Executive Engineer
Kodigehalli Sub Division
Bruhat Bangalore Mahanagara...
Bangalore - 560 092

****End of Report****

CIVIL Pro Sig. Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com